





Product description

[
∎ Use	 Resygum V is an adhesive elastomer profile for the installation of insulating glazing. Its "grooved" profile enables installing (by compression of the strands) with a low constraint, thus avoiding glazing to break. Installation of insulation glass in workshop and on building sites.

Product properties

Resistance	 against tear at 10 mm/mn against pressure at 23°C 	0,2 MPa 0.14 MPa	
	• against UV	excellent	
Temperature	of application	+ 5°C ≤ T ≤ + 40°C	
	• of service	$-30^{\circ}C \le T \le +80^{\circ}C$	
Elongation at break		> 250 %	
Diffusion of the		lm ≤ 4 mm	
components		Nm ≤ 3 mm	

Test reports

(
Test reports	 Qualification of weather-stripping profiles as per CTBA test report (ref. 98/PC L/258/133 and 133 1 of 30/06/99).
Tests	 Rheological stability to thermal shocks 130°C (5 cycles) CTBL 114/ XPP 23 310/ NF P 85 553 Not hardening with thermal shocks at 130°C (5 cycles) CTBL 114/ XPP 23 310/ NF P 85 553

OLIN SAS

25 avenue de l'industrie 69960 CORBAS (France) Tél: +33 (0) 4 72 23 18 00 - Fax : +33 (0) 4 72 23 18 18 www.olin.fr



EXANCHEITE ISOLATION



Instruction for use

(
Surface	The surface must be clean, dry and free of dust.
preparation	 Press Resygum V until all wrinkles disappear to obtain a good adherence on the support. Please do not cover angles with tape. Please do not create extra thickness with the product.
Application	 For the installation of glazing in a workshop, the use and the installation must conform with standards NF P 23 305 and XP P 23 310. For the installation of glazing on the jobsite, the use and the application must conform with standards NF P 78 201 1 (DTU n°39) and NF P 23 305.

Standard packaging

Otantial	packaging	
Packaging	• rolls with sections of 8x3 mm • 10x3 mm • 12x2,5 mm • 15x3 mm	
Standard colours	• wood • black	
Safety		
Safety instructions	 Avoid contact with skin. In the event of contact with eyes, clean immediately with water and obtain medical attention. Keep out of the reach of children. Consult the Safety Data Sheet of the product on www.olin.fr. 	
shelf life	- Storage	
Conditions	• 18 months from production date, in original unopened packaging and protected from humidity.	

• Store in a well ventilated room and at a maximum temperature of 30°C.

Recommendations

Our technical advices on the use of the product are expressed either orally, in writing or by means of tests. They are given to the best of our knowledge. They constitute simple indications which do not engage our responsibility. These values are given as an indication only and they cannot, in any case, be regarded as specifications. Insofar as it is not possible for us to control the use of the product and taking into account the diversity of materials and the possible uses, the users will have to carry out the tests necessary to determine if the product is suited for the specific use for which it is intended. It is up to the users to respect local legislation and to obtain the homologations and authorizations that are eventually required. Please check with our Customer Service that you have the current version of the Technical Data Sheets and of the Safety Data Sheets of the products you



OLIN SAS

25 avenue de l'industrie 69960 CORBAS (France) Tél: +33 (0) 4 72 23 18 00 - Fax : +33 (0) 4 72 23 18 18 www.olin.fr